

IN THE SPECIFICATION

Page 36, paragraph bridging pages 36 and 37, beginning at line 12, please amend to read as follows:

100 ml of aqueous composition was prepared in a beaker, and a slide glass having an area of 10 cm² was dipped therein for 20 seconds and then dried completely by leaving the slide glass at room temperature for 15 minutes. This procedure was conducted repeatedly 10 times. 0.5 g of model stain (mixture of oleic acid and rapeseed oil in the mass ratio of 1:1) was applied, in a spot form, on the surface of the slide glass thus treated. The slide glass onto which the model stain had been applied was placed at the bottom of a water tank slowly such that the model stain was not washed away, and then the water tank was filled slowly with the aqueous composition such that the slide glass was not directly splashed with the solution, during which the proportion of an area where the model stain was removed from the surface of the ~~ceramic tile~~ slide glass was determined and evaluated in the following 5 stages. The percent of removal of the stain was the average of 5 measurements.